


IN THE CLAIMS:

Please amend claims 1-9. Please cancel claims 11-20 without prejudice or disclaimer. Please note that all claims currently pending and under consideration in the above-referenced application are shown below. Please enter these claims as amended. This listing of claims will replace all prior versions and listings of claims in the application.


Listing of Claims:

1. (Currently amended) A print medium comprising an ink-receiving layer and a coated paperbase, the ink-receiving layer ~~comprising~~ consisting of at least one hydrophilic polymer, at least one cross-linking agent, at least one mordant, inorganic particles, a at least one nonionic siloxane copolymer-surfactant surfactant, and at least one nonsiloxane surfactant, wherein the at least one hydrophilic polymer is selected from the group consisting of polyvinyl alcohol, a copolymer of polyvinylalcohol with polyethyleneoxide, a copolymer of polyvinylalcohol with polyacrylic or maleic acid, acetoacetylated polyvinylalcohol, polyethylene oxide, hydroxyethyl cellulose, hydroxypropylmethyl cellulose, poly(N-ethyl-2-oxazoline), casein, starch, agar, carrageenan, cellulose, carboxymethyl cellulose, dextran, pullulan, gelatin, derivatives thereof, and mixtures thereof.

2. (Currently amended) The print medium of claim 1, wherein the at least one nonionic siloxane copolymer surfactant comprises the following structure:



wherein A is $-\text{CH}_3$ or B, and B is a C_1 to C_{10} straight chain or branched primary or secondary hydroxy terminated alkylene group, and x and y are such as to provide a molecular weight greater than about 1000.



wherein m, n, x, and y are such as to provide a molecular weight greater than about 1000, wherein Z is H, -CH₃, or a C₁ to C₁₀ straight chain or branched primary or secondary hydroxy terminated alkylene group, and wherein the structure contains at least one polyethyleneoxide group.

4. (Currently amended) The print medium of claim 1, wherein the surface tension of the at least one nonionic siloxane copolymer surfactant is from about 20 dyne/cm to about 35 dyne/cm.

5. (Currently amended) The print medium of claim 1, wherein the hydrophilic/hydrophobic balance value (HLB) of the at least one nonionic siloxane copolymer surfactant is from about 10 to about 30.

6. (Currently amended) The print medium of claim 1, wherein the ~~weight percent (wt %) of the~~ at least one nonionic siloxane copolymer surfactant is present at from about ~~0.05 wt %~~ 0.05 weight percent of a total weight of the ink-receiving layer to about ~~2 wt %~~ 2 weight percent of the total weight of the ink-receiving layer.

7. (Currently amended) The print medium of claim 1, wherein the at least one nonionic siloxane copolymer surfactant has a molecular weight of greater than about 1000.

8. (Currently amended) The print medium of claim 1, wherein the ~~ink-receiving layer further~~ at least one nonsiloxane surfactant comprises a nonionic or anionic nonsiloxane surfactant, wherein the nonionic or anionic nonsiloxane surfactant is present in a concentration that is less than the concentration of the at least one nonionic siloxane copolymer surfactant present in the ink-receiving layer.

9. (Currently amended) The print medium of claim 1, wherein the at least one nonionic siloxane copolymer surfactant comprises at least one polysiloxane-polyethylene oxide compound or at least one polysiloxane-polyethylene oxide-polypropylene oxide compound.

10. (Original) The print medium of claim 1, wherein the coated paperbase comprises a coated paper, a cast-coated paper, or a commercial offset paper.

Claims 11-20 (Canceled)